

## TERMOMELT ECOTOP 10

### USE

#### **Packaging**

Product based on catalyzed polyolefin, assure very high performance with low consumption.

Gluing of cases, trays forming, closing carton and cases.

Gluing of a wide range of paper and cardboard, also heavy, rigid, printed, coated, water varnished, PE coated or treated.

Suitable for gluing straw on brik, excellent machining, no oxidise, no char, odourless, without filaments.

Formulated and optimized for use in new tankless, on-demand systems Nordson Freedom™ and Graco Invisipac® (officially approved and certified)

#### **Shopping Bags**

Forming and reinforcing handles, gluing patch and bottom of a wide range of paper, also coated, printed and water varnished.

### SPECIFICATION

#### **Type of adhesive**

Hotmelt

#### **Color**

Transparent white

#### **Viscosity at 170°C**


900 - 1100 mPas

#### **Softening Point (R&B)**

108°C ± 5°C

#### **Open time**

Short



### REGULATORY STATUS

Complies to:

FDA 21 cfr 175.105 adhesives;

FDA 21 cfr 176.170 direct contact with aqueous and fatty foods;

FDA 21 cfr 176.180 direct contact with dry foods.

### WORK INSTRUCTION

#### **Temperature**

150° - 190°C

#### **Type**

Nozzle, disc

#### **Cleaning**

Use Leuenberger TOPCLEAN to clean the external metallic surfaces.

### DELIVERY FORM

Granules in 25Kg bags

### HEALTH & SAFETY REGULATIONS

See material safety data sheet

### SHELF LIFE AND STORAGE CONDITIONS

Up to 12 months in closed original packaging and under normal dry storage conditions

Leuenberger+C Spa | Via De Chirico, 2 | 26013 Crema (CR) - Italy

Phone +39 0373 631100 | Fax +39 0373 631120 | [www.leuenberger.it](http://www.leuenberger.it)

The information provided herein, especially recommendations for the use and the application of our products, is based upon our knowledge and experience. Due to different materials used and to varying working conditions beyond our control, we strongly recommend to carry out extensive trials to test the suitability of our products for the intended processes and applications. We do not accept any liability arising from either the above statements or any oral advice unless attributable to intention or gross negligence on our part.